



Pavestone UK Limited
Burford Quarry, Burford Road
Brize Norton, Oxfordshire.
OX18 3WN

13

EN 1341 : 2012
Indian Limestone – Abbey

Pavestone Indian Limestone Flags are intended for use in and around domestic dwellings as a paving material suitable for home patios, pathways and internal floor coverings. Pavestone Indian Limestone Flags are not designed for vehicular trafficking or for commercial properties.

	Test Results	Protocol
Flexural Strength. Lowest Expected Value (MPa)	19.2 (mean)	EN – 12372:2006
Frost Resistance Flexural Strength before/ after 48 cycles freeze/ thaw (MPa)	20.2 / 21.4	EN – 12372:2006 EN – 12371:2001
Slip / Skid Resistance – Dry	57 (mean)	EN – 14231:2003
Slip / Skid Resistance – Wet	42 (mean)	EN – 14231:2003
Durability – Resistance to wear (mm)	12.0 (mean)	EN – 14157:2004
Water Absorption by wt (%)	0.15 (mean)	EN – 13755:2001
Release of dangerous substances	NPD	

Manufactured in Kota, Rajasthan. India