



Pavestone UK Limited
Burford Quarry, Burford Road
Brize Norton, Oxfordshire.
OX18 3WN

13

EN 1341 : 2012
Indian Sandstone – Piazza Oasis

Pavestone Indian Sandstone Flags are intended for use in and around domestic dwellings as a paving material suitable for home patios, pathways and internal floor coverings. Pavestone Indian Sandstone Flags are not designed for vehicular trafficking or for commercial properties.

| | Test Results | Protocol |
|---|--------------|------------------------------------|
| Flexural Strength (MPa) | 34.8 (mean) | EN – 12372:2006 |
| Frost Resistance Flexural Strength after 48 cycles freeze/ thaw (MPa) | 32.8 (mean) | EN – 12372:2006 EN – 12371:2001 |
| Compressive Strength (kg/cm ²) | 565.4 (mean) | EN – 12372:2006 |
| Slip / Skid Resistance – Dry | 74 (mean) | EN – 14231:2003 |
| Slip / Skid Resistance – Wet | 60 (mean) | EN – 14231:2003 |
| Durability – Resistance to wear (mm) | 6.2 (mean) | EN – 14157:2004 |
| Water Absorption by wt (%) | 0.95 (mean) | EN – 13755:2001 |
| Release of dangerous substances | NPD | |

Manufactured in Kota, Rajasthan. India